

Quality specification ACTIVATED CARBON

Delivery quantity 470-500 kg big-bag

Property	Unit	Min	Max	Test-Method
CTC activity (CCI4)		50,0	-	
Butane Activity		19	-	
Total surface area BET	m ² /g	900	1000	
Iodine number	mg/g	900	-	
Apparent density	g/cm ³	0,48	0,54	
Bulk fill density	kg/m ³	470		
Hardness	%	90,0	-	
Ash	%	-	15,0	
Moisture	%	-	5,0	